













TILE PERFORMANCE DATA

COLORED-BODY PORCELAIN TILES - RECTIFIED, ONE CALIBER
CLASSIFICATION IN ACCORDANCE WITH ANSI A137.1: 2012 (P1 CLASS).

TECHNICAL FEATURE	ASTM TEST	VALUE REQUIRED ANSI A 137.1-2012	CAESAR AVERAGE VALUE
 Facial dimension	ASTM C-499	±0,5% o ±2,0 mm	In accordance to ANSI A 137.1-2012
 Thickness	ASTM C-499	0,040 inch max (1 mm)	
 Wedging	ASTM C-502	≤ 0,5% (+/- 2 mm)	
 Warpage diagonal	ASTM C-485	≤ 0,5% (+/- 2 mm)	
 Warpage edge (for tile <610x610 mm)	ASTM C-485	±0,40% or ±1,3 mm	
 Warpage edge (for tile >610x610 mm)	ASTM C-485	±0,40% or ±1,8 mm	
 Water absorption	ASTM C-373	≤ 0,5%	Passed "impervious tiles" Class P1
 Breaking strength	ASTM C-648	≥ 250 lbs (>=1113 N)	>=400 lbs
 Freeze thaw	ASTM C-1026	No damages	In accordance
 Chemical resistance	ASTM C-650	As reported	Unaffected
 MOHS hardness			Coeff. 6
 BOOT 3000 DCOF *	BOOT 3000	0,42	In accordance

Average values referred to the last two years of production and related to the matt finish of the product.

Values relate to the matt finish of the product and to tests carried out by certified external laboratories, whose results are available upon request at Headoffice. Be sure to use the same caliber tiles.

Color reproductions may vary from actual products.

* Due to the intrinsic nature of porcelain stoneware tiles, please note that the coefficient of friction may vary within the same production lot or from one production lot to the other. Caesar products can become slippery when wet. We recommend to always keep the surface dry.